(c)2001-2005 Mineral Data Publishing, version 1

Crystal Data: Orthorhombic. *Point Group:* 222. Rarely as euhedral crystals, equant to short prismatic along [010], to 3 mm, terminated by many forms, both left- and right-handed; typically in radial fibrous aggregates, as botryoidal to reniform crusts, massive. *Twinning:* Rare on {001}.

Physical Properties: Fracture: Uneven. Tenacity: Brittle. Hardness = 4.5 D(meas.) = 4.33 D(calc.) = 4.29

Optical Properties: Subtranslucent. *Color:* Grass-green to yellowish green, pistachio-green, emerald-green; in transmitted light, pale green to yellowish green, commonly zoned. *Streak:* Green. *Luster:* Vitreous to somewhat greasy.

Optical Class: Biaxial (+), may be biaxial (-), commonly zoned. Pleochroism: X = colorless to green; Y = pale greenish to yellow-green; Z = pale bluish to blue-green. Orientation: X = c; Y = b; Z = a. Dispersion: r > v, strong, to r < v, moderate. $\alpha = 1.778-1.800$ $\beta = 1.795-1.831$ $\gamma = 1.801-1.846$ $2V(\text{meas.}) = 0^{\circ}-90^{\circ}$

Cell Data: Space Group: $P2_12_12_1$. a = 7.38-7.40 b = 9.21-9.24 c = 5.82-5.84 Z = 4

X-ray Powder Pattern: Higgins mine, Bisbee, Arizona, USA. 2.84 (10), 2.59 (10), 3.14 (9), 1.609 (7), 1.720 (6), 4.10 (5), 2.56 (5)

Chemistry:	(1)	(2)	(3)		(1)	(2)	(3)
P_2O_5	8.81	1.4		ZnO		0.7	
$\overline{As_2O_5}$	30.68	42.6	44.27	CaO	21.36	21.6	21.61
V_2O_5	1.78			H_2O	5.61	[3.6]	3.47
CuO	31.76	30.1	30.65	Total	100.00	[100.0]	100.00

(1) Hinojosa de Córdoba, Spain. (2) Higgins mine, Bisbee, Arizona, USA; by electron microprobe, H_2O by difference. (3) $CaCu(AsO_4)(OH)$.

Polymorphism & Series: Forms three series; with austinite, with cobaltaustinite, and with tangeite.

Mineral Group: Adelite group.

Occurrence: An uncommon secondary mineral in the oxidized zone of copper deposits, typically an alteration product of enargite.

Association: Austinite, olivenite, clinoclase, libethenite, chenevixite, brochantite, malachite, azurite, jarosite, "limonite".

Distribution: Many minor occurrences. Some providing good specimens include: from Hinojosa de Córdoba, Andalusia, Spain. In England, at Wheal Kendall, St. Hilary, and the Hingston Down quarry, Calstock, Cornwall; from Caldbeck Fells, Cumbria. In the USA, at the American Eagle and a number of other mines in the Tintic district, Juab Co., and in the Gold Hill mine, Tooele Co., Utah; from Bisbee, Cochise Co., Arizona; in the Bristol mine, Lincoln Co., and the Empire-Nevada mine, Yerington, Lyon Co., Nevada. From the Ojuela mine, Mapimí, Durango, Mexico. At Collahuasi, Tarapacá, Chile. From the Guchab mine, near Otavi, and at Tsumeb, Namibia.

Name: From the Greek for *lime* and *copper*, as both elements are essential to the composition.

Type Material: Mining Academy, Freiberg, Germany, 21297.

References: (1) Palache, C., H. Berman, and C. Frondel (1951) Dana's system of mineralogy, (7th edition), v. II, 806–809. (2) Berry, L.G. (1951) Observations on conichalcite, cornwallite euchroite liroconite and olivenite. Amer. Mineral., 36, 484–503. (3) Qurashi, M.M. and W.H. Barnes (1954) The structures of the minerals of the descloizite and adelite groups: I – descloizite and conichalcite (part 1). Amer. Mineral., 39, 416–435. (4) Radcliffe, D. and W.B. Simmons, Jr. (1971) Austinite: chemical and physical properties in relation to conichalcite. Amer. Mineral., 56, 1359–1365.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.