Crystal Data: Triclinic. Point Group: 1. Subhedral crystals, to 0.5 mm, platy on {010}, striated | [001]; in fibrous to fine-grained aggregates.

Physical Properties: Cleavage: Perfect on {010}. Tenacity: Extremely brittle. $Hardness = \sim 3$ VHN = 105 (20 g load). D(meas.) = 3.05(10) D(calc.) = 3.00

Optical Properties: Transparent to translucent. Color: Pale rose-red to colorless.

Streak: White. Luster: Vitreous to pearly.

Optical Class: Biaxial (-). Pleochroism: Very weak; colorless to rose-red in thick sections.

Orientation: $X \simeq b$; $Y \simeq a$; $Z \simeq c$; $Z \wedge c = 15^{\circ}$ on $\{010\}$; $Z \wedge c = 6^{\circ}$ on $\{100\}$; $X \text{ almost } \bot \{010\}$.

Absorption: $Z > Y \simeq X$. $\alpha = 1.601(2)$ $\beta = 1.630(2)$ $\gamma = 1.660(2)$ 2V(meas.) = Large.

 $2V(calc.) = 89^{\circ}$

Cell Data: Space Group: $P\overline{1}$. a = 7.944(1) b = 10.691(1) c = 6.770(1) $\alpha = 80.97(1)^{\circ}$ $\beta = 84.20(1)^{\circ}$ $\gamma = 81.85(1)^{\circ}$ Z = 1

X-ray Powder Pattern: Falotta mine, Switzerland.

10.45 (100), 3.051 (24), 3.507 (21), 3.340 (20), 3.011 (17), 2.786 (14), 7.85 (13)

Chemistry:

	(1)	(2)
$\mathrm{As_2O_5}$	50.12	45.40
MnO	39.71	35.03
CaO	0.12	
${\rm H_2O}$	[10.05]	19.57
Total	[100.00]	100.00

- (1) Falotta mine, Switzerland; by electron microprobe, average of five analyses; H_2O by difference.
- (2) $Mn_5(AsO_4)_2(AsO_3OH)_2 \cdot 10H_2O$.

Occurrence: In cavities in radiolarities, formed by metamorphism of manganese oxide ores.

Association: Brandtite, sarkinite, grischunite, bergslagite, manganberzeliite, tilasite.

Distribution: At the Falotta mine, Oberhalbstein, Graubünden, Switzerland.

Name: In honor of Dr. Thomas Geiger (1886–1976), Wiesendangen, Switzerland, who studied Falotta manganese ores.

Type Material: Natural History Museum, Basel, 30804; Basel University, Basel, Switzerland.

References: (1) Graeser, S., H. Schwander, R. Bianchi, T. Pilati, and C.M. Gramaccioli (1989) Geigerite, the Mn analogue of chudobaite: its description and crystal structure. Amer. Mineral., 74, 676-684.