© 2001-2005 Mineral Data Publishing, version 1

**Crystal Data:** Monoclinic. Point Group: 2/m. Crystals exhibit the forms  $\{100\}$ ,  $\{001\}$  and  $\{111\}$ ; all faces in the zone [010] are striated, to 2 mm.

Physical Properties: Hardness = n.d. VHN = n.d. D(meas.) = 4.81 D(calc.) = 4.90

**Optical Properties:** Opaque. Color: Dark gray. Streak: Brownish red. Luster: Submetallic to metallic.

 $R_1-R_2$ : n.d.

**Cell Data:** Space Group:  $P2_1/c$ . a = 17.441(5) b = 7.363(2) c = 32.052(7)  $\beta = 105.03(7)^{\circ}$  Z = 4

X-ray Powder Pattern: Alšar, Macedonia.

3.076 (100), 3.368 (90), 2.948 (75), 2.186 (75), 4.004 (65), 4.147 (45), 3.107 (5)

Chemistry:

	(1)	(2)
Tl	32.76	34.81
$\operatorname{Sb}$	22.88	20.74
As	20.46	20.42
$\mathbf{S}$	24.33	24.03
Total	100.43	100.00

- (1) Alšar, Macedonia; by electron microprobe; corresponds to  $Tl_{4.65}Sb_{5.45}As_{7.92}S_{22.00}$ .
- (2)  $Tl_5Sb_5As_8S_{22}$ .

Occurrence: In a hydrothermal As-Tl deposit.

**Association:** Simonite, TlHgAsS<sub>3</sub> (christite or routhierite), realgar.

Distribution: From Alšar (Allchar), near Rošden, Macedonia [TL].

**Name:** To honor a Slovenian geologist or mining engineer named Rebula, who discovered the mineral.

Type Material: n.d.

**References:** (1) Balić-Žunić, T., S. Šćavničar, and P. Engel (1982) The crystal structure of rebulite,  $Tl_5Sb_5As_8S_{22}$ . Zeits. Krist., 160, 109–125. (2) (1983) Amer. Mineral., 68, 644 (abs. ref. 1). (3) Rieck, B. (1993) Allchar, Macedonia. Mineral. Record, 24, 437–449.