Babefphite $BaBe(PO_4)F$

(c)2001-2005 Mineral Data Publishing, version 1

Crystal Data: Triclinic, pseudotetragonal. *Point Group:* 1. As anhedral, equant to flattened grains, to 1.5 mm; may be in aggregates.

Physical Properties: Tenacity: Very brittle. Hardness = [3.5] VHN = 140-200 D(meas.) = 4.31 D(calc.) = 4.325

Optical Properties: Transparent. Color: White. Luster: Vitreous to greasy. Optical Class: Biaxial; pseudouniaxial (+). Orientation: Negative elongation. $\omega = 1.629(2)$ $\epsilon = 1.632(2)$

Cell Data: Space Group: P1. a = 6.889(3) b = 16.814(7) c = 6.902(3) $\alpha = 90.01(3)^{\circ}$ $\beta = 89.99(3)^{\circ}$ $\gamma = 90.32(3)^{\circ}$ Z = 8

X-ray Powder Pattern: Aunik deposit, Russia. 3.190 (10), 2.163 (10), 1.516 (10), 2.760 (8), 2.440 (7), 2.033 (7), 1.135 (7b)

Chemistry:

	(1)	(2)
P_2O_5	26.55	27.26
$\mathrm{Fe_2O_3}$	0.3	
${\rm BeO}$	11.63	9.61
CaO	0.00	
BaO	56.50	58.90
F	7.27	7.30
$\mathrm{H_2O}$	[0.64]	
$-O = F_2$	3.05	3.07
Total	[99.84]	100.00

(1) Aunik deposit, Russia; by microchemical analysis, with $(OH)^{1-}$ for charge balance, corresponds to $Ba_{0.99}Be_{1.20}(PO_4)_{1.00}[F_{1.02}(OH)_{0.36}]_{\Sigma=1.38}$. (2) $BaBe(PO_4)F$.

Occurrence: In eluvium directly above rare-metal skarn deposits associated with alkaline intrusions.

Association: Zircon, ilmenorutile, fluorite, phenakite, scheelite, bertrandite, albite, microcline, quartz.

Distribution: Occurs in the Aunik fluorite-rare metals deposit, Buryatia, Siberia, Russia.

Name: For BArium, BEryllium, Fluorine, and PHosphorous in the composition.

Type Material: A.E. Fersman Mineralogical Museum, Academy of Sciences, Moscow, Russia, 72021.

References: (1) Nazarova, A.S., N.N. Kuznetsova, and D.P. Shashkin (1966) Babefphite, a barium-beryllium fluoride-phosphate. Doklady Acad. Nauk SSSR, 167, 895–897 (in Russian). (2) (1966) Amer. Mineral., 51, 1547 (abs. ref. 1). (3) Simonov, M.A., Y.K. Yegorov-Tismenko, and N.V. Belov (1980) Use of modern X-ray equipment to solve fine problems of structural mineralogy by the example of the crystal structure of babefphite $BaBe(PO_4)F$. Kristallografiya (Sov. Phys. Crystal.), 25, 28–30.